

Stratum 500


Collection	Stratum	
Style Number	023UV	
Construction	Multilayer WPC With Attached Cork Underlayment	
class	Class III, Type B	
Attached Underlayment	Cork	
Finish	ExoGuard®	
	U.s.	Metric
Nominal Dimensions	5 in w x 48 in l	13 cm w x 122 cm l
Actual Dimensions	4.96 in w x 48.03 in l	12.60 cm w x 122.00 cm l
Wear Layer Thickness	20 mil (0.02 in)	0.51 mm
Overall Product Thickness	0.315 in	8 mm
Edge Profile	Micro-Bevel	
Installation Type	Click	
Installation	Floating Or Direct Glue	
Recommended Adhesive	4200 Resilient Tile 4 Gallon, 2200 Resilient Tile 4 Gallon, 4151 Multi-Use Premium 4 Gallon or SHAW 4100 4 GAL	



Packaging

Pieces Per Box	16 pcs	
Area Per Box	26.47 sq ft	2.46 sq m
Weight Per Box	44.09 lbs	20 kg

Recommended Installation Method



Coordinating Products

None: Stratum 1200  
COREtec: Stratum 700, Stratum XI, Stratum Eiris, Stratum Linear, Defined

Performance + Testing

Residual Indentation (Astm F1914)	Passes
Resistance To Heat (Astm F1514)	Passes
Resistance To Light (Astm F1515)	Passes
Resistance To Chemicals (Astm F925)	Passes
Coefficient Of Friction (Astm D2407, Slip Resistance)	≥0.5, meets the recommended static coefficient of friction for ADA walking surfaces
Test Reports may be included or listed by the manufacturing/inventory style number as opposed to the noted selling style number.	

Warranties

15 Year Commercial Limited








Attributes + Certifications

Health & Wellbeing	
Material Ingredient Transparency	Health Product Declaration (HPD)   1000 ppm Disclosure
Climate Impact	
Environmental Product Declaration (EPD)	3rd Party Certified in Accordance with ISO 14025, EN 15804, & ISO 21930:2017
Total Recycled Content	0% (Pre-Consumer 0%   Post-Consumer 0%)
Global Product Assessment	FloorScore®   Certified Greenguard (Certification, Gold, Private Label)   Certified Country of Origin   China

Green Leed Contribution Credit

MR Credit: Building Product Disclosure and Optimization Material Ingredients - Option 1: Material Ingredient Reporting	Health Product Declaration (HPD)   100 Ppm Disclosure
MR Credit: Building Product Disclosure and Optimization Environmental Product Declarations - Option 1: Environmental Product Declaration (EPD)	3rd Party Certified in Accordance with ISO 14025, EN 15804, & ISO 21930:2017
EQ Credit: Low Emitting Materials Option 1: Product Category Calculations	FloorScore & Greenguard Gold Certified
Installation Guidelines	Please visit <a href="http://www.shawcontract.com">www.shawcontract.com</a> for the most current warranty information. Specifications are subject to nominal manufacturing variance. Material supply and/or manufacturing processes may necessitate changes without notice.  This product is an exclusive design and may not be duplicated in any manner. Use of this design in the creation of another product design is also strictly prohibited. *****Allowable spend is domestic (US) spend in categories in which we have diverse suppliers from which to choose. Compared to non-allowable spend which includes categories in which we do not have domestic, small or diverse suppliers available to meet our needs.  Visit <a href="http://shawcontract.com/testing">shawcontract.com/testing</a> for more information.
Maintenance Guidelines	

Available Colorways

					
Acacia 00201 V4 - Substantial Variation	Mocha Oak 00202 V3 - Moderate Variation	Vintage Oak 00205 V2 - Slight Variation	Weathered Oak 00206 V3 - Moderate Variation	Limerick Oak 00207 V3 - Moderate Variation	Apalachicola Pine 00501 V4 - Substantial Variation
					
Targhee Walnut 00503 V1 - Uniform Appearance	Chattahoochee Oak 00504 V4 - Substantial Variation	Allegheny Maple 00505 V4 - Substantial Variation	Wimena Pine 00506 V2 - Slight Variation	Oconee Walnut 00507 V4 - Substantial Variation	Gallatin Hickory 00508 V4 - Substantial Variation

Color and Visual Variation Index

Shade and texture variation is inherent in all resilient products and can vary significantly from piece to piece. Samples should be used to assess color.

