

Stratum Eiris


Collection	Stratum	
Style Number	053UV	
Construction	Multilayer WPC With Attached Cork Underlayment	
class	Class III, Type B	
Attached Underlayment	Cork	
Finish	ExoGuard®	
	U.s.	Metric
Nominal Dimensions	7 in w x 59 in l	18 cm w x 150 cm l
Actual Dimensions	7.09 in w x 59.06 in l	18.01 cm w x 150.01 cm l
Wear Layer Thickness	30 mil (0.03 in)	0.76 mm
Overall Product Thickness	0.335 in	8.5 mm
Edge Profile	Micro-Bevel	
Installation Type	Click	
Installation	Floating Or Direct Glue	
Recommended Adhesive	, 4200 Resilient Tile 4 Gallon, 2200 Semi-Wet Resilient 4 Gallon Pail, 2200 Semi-Wet Resilient 1 Gallon Pail, , 4151 Multi-Use Premium 4 Gallon or Shaw 4100	



Packaging

Pieces Per Box	6 pcs	
Area Per Box	17.43 sq ft	1.62 sq m
Weight Per Box	33.95 lbs	15.4 kg

Recommended Installation Method



Coordinating Products

COREtec: Stratum 500, Stratum 700, Stratum XI, Defined, Stratum Nordic

performance + testing

residual indentation (ASTM F1914)	Passes
resistance to heat (ASTM F1514)	Passes
resistance to light (ASTM F1515)	Passes
resistance to chemicals (ASTM F925)	Passes
radiant panel (ASTM E648)	Passes, Class I

Test Reports may be included or listed by the manufacturing/inventory style number as opposed to the noted selling style number.

Warranties

[15 Year Commercial Limited](#)

Attributes + Certifications

Health & Wellbeing	
Material Ingredient Transparency	Health Product Declaration (HPD) 1000 ppm Disclosure
Indoor Air Quality	FloorScore® Certified
Climate Impact	
Environmental Product Declaration (EPD)	3rd Party Certified in Accordance with ISO 14025, EN 15804, & ISO 21930:2017
Embodied Carbon (Cradle to Gate)	11.5 Kg Co ₂ /M ²
Total Recycled Content	41% (Pre-Consumer 41% Post-Consumer 0%)
Global Product Assessment	Country of Origin China

WELL V2 Contribution Credit

X01 Fundamental Material Precautions Part 1: (C): Restrict Asbestos Precondition	Absence of Asbestos
X08 Hazardous Material Reduction Part 1: Limit Hazardous Materials Optimization – 1 pt	Absence of Heavy Metals
X10 Volatile Compound Reduction Part 1 (A): Manage Volatile Organic Compounds (VOCs) Optimization – 1 pt	Absence of Halogenated Flame Retardants
Part 2: Manage Semi-Volatile Organic Compounds (SVOCs) Optimization – 1 pt	Ortho-Phthalates
X11 Long Term Emissions Control Part 2: Flooring Optimization – 1 pt	Greenguard Gold Certificate

Leed Contribution Credit

MR Credit: Building Product Disclosure and Optimization Material Ingredients - Option 1: Material Ingredient Reporting	Health Product Declaration (HPD) 100 Ppm Disclosure
MR Credit: Building Product Disclosure and Optimization Environmental Product Declarations - Option 1: Environmental Product Declaration (EPD)	3rd Party Certified in Accordance with ISO 14025, EN 15804, & ISO 21930:2017
EQ Credit: Low Emitting Materials Option 1: Product Category Calculations	FloorScore® Certified

[Installation Guidelines](#)


[Maintenance Guidelines](#)

Please visit www.shawcontract.com for the most current warranty information. Specifications are subject to nominal manufacturing variance. Material supply and/or manufacturing processes may necessitate changes without notice.


This product is an exclusive design and may not be duplicated in any manner. Use of this design in the creation of another product design is also strictly prohibited.

Visit shawcontract.com/testing for more information.

Available Colorways




Cinnamon 06001
LRV 14.9 | L* 45.47
V3 - Moderate Variation




Tannery Brown 06002
LRV 10.3 | L* 38.4
V2 - Slight Variation




Summer Truffle 06003
LRV 9.2 | L* 36.34
V2 - Slight Variation




Abyss 06004
LRV 6.6 | L* 30.97
V3 - Moderate Variation




Ivory 06005
LRV 25.4 | L* 57.48
V2 - Slight Variation



Bone 06006
LRV 23 | L* 55.05
V4 - Substantial Variation



Morchella 06007
LRV 9.5 | L* 36.84
V2 - Slight Variation



Cremini 06008
LRV 35.6 | L* 66.23
V3 - Moderate Variation

Color and Visual Variation Index

Shade and texture variation is inherent in all resilient products and can vary significantly from piece to piece. Samples should be used to assess color.

