



**Professional  
Testing  
Laboratory  
Inc.**

## TEST REPORT

<b>TEST NUMBER</b>	0080591
<b>DATE</b>	10/14/03
<b>PAGE</b>	1 of 2

<b>CLIENT</b>	STILE/DIVISION OF SHAW
---------------	------------------------

<b>TEST METHOD CONDUCTED</b>	ASTM E662-01 Specific Optical Density of Smoke Generated by Solid Materials, also referenced as NFPA 258
------------------------------	--

DESCRIPTION OF TEST SAMPLE	
<b>IDENTIFICATION</b>	59357 Blox EW 24
<b>COLOR</b>	-----
<b>ROLL</b>	SO-L2262
<b>CONSTRUCTION</b>	Textured Loop Pile
<b>FIBER</b>	-----
<b>BACKING</b>	EcoWorx
<b>REFERENCE</b>	TEST NO: 092903-5


### TEST RESULTS

<b>FLAMING</b>	118
----------------	-----

### GENERAL PRINCIPLE

This procedure is designed to measure the specific optical density of smoke generated by the test specimen within a closed chamber. Each specimen is exposed to an electrically heated radiant-energy source positioned to provide a constant irradiance level of 2.5 watts/square cm on the specimen surface. Measurements are recorded through a photometric system employing a vertical beam of light and a photo detector positioned to detect the attenuation of light transmittance caused by smoke accumulation within the chamber. The light transmittance measurements are used to calculate specific optical density, a quantitative value which can be factored to estimate the smoke potential of materials. Two burning conditions can be simulated by the test apparatus. The radiant heating in the absence of ignition is referred to as the Non-Flaming Mode. A flaming combustion in the presence of supporting radiation constitutes the Flaming Mode.

This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc., shall not be used under any circumstance in advertising to the general public.





**Professional  
Testing  
Laboratory  
Inc.**

# TEST REPORT

**TEST NUMBER** 0080591

**DATE** 10/14/03

**PAGE** 2 of 2

**CLIENT**

STILE/DIVISION OF SHAW

**TEST METHOD CONDUCTED**

ASTM E662-01 Specific Optical Density of Smoke Generated by Solid Materials, also referenced as NFPA 258

## DESCRIPTION OF TEST SAMPLE

**IDENTIFICATION** 59357 Blox EW 24

**COLOR** -----

**ROLL** SO-L2262

**CONSTRUCTION** Textured Loop Pile

**FIBER** -----

**BACKING** EcoWorx

**REFERENCE** TEST NO: 092903-5

## CONDITIONS

**PREDRYING OF TEST SAMPLE  
CONDITIONING OF TEST SAMPLE**

24 Hours at 140 degrees F  
24 Hours at 70 degrees F and  
50% relative humidity

**FURNACE VOLTAGE  
CHAMBER TEMPERATURE  
TEST MODE**

113 V  
95 degrees F  
Flaming

**IRRADIANCE  
CHAMBER PRESSURE**

2.5 watts/sq cm  
3" H2O

**AVERAGE MAXIMUM DENSITY CORRECTED (Dmc)**

118

	1	2	3
Maximum Density (Dm)	123	158	146
Time to Dm (minutes)	4.5	3.5	8.5
Clear Beam (Dc)	23	23	26
Corr. Max Density (Dmc)	100	135	120
Density at 1.5 minutes	5	16	10
Density at 4.0 minutes	122	155	145
Time to 90% Dm (minutes)	3.5	3.0	3.0
Specimen Weight (grams)	19.6	19.5	18.5

**AVERAGE SPECIFIC OPTICAL DENSITY AT 4.0 MINUTES: 141**

**APPROVED BY:**

*Gary Asbury*

This facility is accredited by the National Voluntary Laboratory Accreditation Program for the specific scope of accreditation under Lab Code 100297. This accreditation does not constitute an endorsement, certification, or approval by NIST or any agency of the United States Government for the product tested. This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory, Inc., shall not be used under any circumstance in advertising to the general public.

