



TEST REPORT

CLIENT:

Company:	Shaw Hard Surfaces	Report Number:	68136A
Address:	PO Drawer 2128	Lab Test Number:	2831-9205
	Dalton, GA 30722	Test Completion Date:	8/01/2016
		Report Date:	8/03/2016
		Page:	1 of 1
Requested By:	Stuart Bartenfield		

TEST MATERIAL:

Material Type:	Resilient Flooring	Date Received:	06/22/2016
Material Condition:	EXCELLENT:	XXX	GOOD:
		POOR:	REJECTED:
Style:	V0317 Stone Effect	Lot #:	N/A
Thickness:	N/A	Test #:	R-160620-29553
		Size:	N/A

TESTING METHODS REQUESTED:

Testing Services, Inc. was instructed by the client to perform the following testing....			
Standard:	ASTM F1515	Test Method:	Standard Test Method for Measuring Light Stability of Resilient Flooring by Color Change

SAMPLING PLAN:

Sampling Date:	06/22/2016
<ul style="list-style-type: none"> Specimen sampling is performed in the sampling department at TSI. The sampling size of specimens is determined by the test method requirements. In the event a specific sampling size is not called for, a determination will be made based on previous testing experience, and approved for use by an authorized manager. All samples are subjected to the outside environmental conditions of temperature and relative humidity. Sample requiring pre-determined exposure to specified environmental conditions based on a specific test method, take place in the departments in which they are tested 	

DEVIATION FROM TEST METHOD:

State reason for any Deviation from, Additions to, or Exclusions From Test Method.
None

TEST OVERVIEW:

This test procedure determines the color change of the resilient flooring after exposure to accelerated lightfastness.

Three specimens of the resilient flooring were read by Hunter Colorquest instrument and its color matrix, ΔE , recorded. The specimens were then placed into an Atlas Ci35 fadeometer with the following settings:

Lamp Cooling: Water
 Light Cycle: Continuous
 Temp: 145°F
 RH: 30%
 Filter (Outer): Soda Lime
 Filter (Inner): Borosilicate
 Irradiance: 1.10 w/cm²

The specimens were exposed for 300 hours, removed, and re-read by the colorquest for ΔE color change.

TEST DATA:

Average ΔE Reading After Exposure	Requirement	Comment
1.34	$\Delta \leq 8.0$	Passes

Approval:

Erle Miles, Jr. VP,
 Testing Services, Inc

Form:	Rev:	Revision Date:	Page 1 of 1
Release Date:	Control Type: Electronic – Expires 24 hours after this date: Aug. 16, 16 Printed copies are uncontrolled		

OUR LETTERS AND REPORTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAR PRODUCTS. THESE LETTERS AND REPORTS ARE FOR THE USE ONLY OF THE CLIENT TO WHOM THEY ARE ADDRESSED AND THEIR COMMUNICATION TO ANY OTHERS OR THE USE OF THE NAME TESTING SERVICES, INC. MUST RECEIVE OUR PRIOR WRITTEN APPROVAL. OUR REPORTS, LETTERS, NAME, SEALS, OR INSIGNIA ARE NOT UNDER ANY CIRCUMSTANCES TO BE USED IN ADVERTISING TO THE GENERAL PUBLIC.

PO Box 2041
 Dalton, GA 30722-2041
 (706) 226-1400
 tsioffice@optilink.us