



TEST REPORT

CLIENT:

Company:	Shaw Hard Surfaces	Report Number:	75529A
Address:	PO Drawer 2128	Lab Test Number:	3054-7937
	Dalton, GA 30722	Test Completion Date:	10/11/2018
		Report Date:	11/5/2018
		Page:	1 of 1
Requested By:	Stuart Bartenfield		

TEST MATERIAL:

Material Type:	Resilient Flooring	Date Received:	9/12/2018
Material Condition:	EXCELLENT: <input checked="" type="checkbox"/> GOOD: <input type="checkbox"/> POOR: <input type="checkbox"/> REJECTED: <input type="checkbox"/>		
Style #	V1529/0529V/VG055		
Test #	R-180830-52687		

TESTING METHODS REQUESTED:

Testing Services Inc. was instructed by the client to test for the following...			
Standard:	ASTM E648, NFPA 253, FTM Standard 372	Test Method:	Standard Test Method for Critical Radiant Flux of Floor Covering Systems Using a Radiant Heat Energy Source

SAMPLING PLAN:

Sampling Date:	9/12/2018
<ul style="list-style-type: none"> Specimen sampling is performed in the sampling department at TSI. The sampling size of specimens is determined by the test method requirements. In the event a specific sampling size is not called for, a determination will be made based on previous testing experience, and approved for use by an authorized manager. All samples are subjected to the outside environmental conditions of temperature and relative humidity. Sample requiring pre-determined exposure to specified environmental conditions based on a specific test method, take place in the departments in which they are tested 	

DEVIATION FROM TEST METHOD:

State reason for any Deviation from, Additions to, or Exclusions From Test Method.
None

TEST SCOPE:

This test method measures the critical radiant flux of horizontally mounted floor-covering systems exposed to a flaming ignition source positioned on a graded radiant heat energy environment within an enclosed chamber. The results are designed to provide a basis for estimating one aspect of fire behavior of a flooring system.

TEST SUMMARY:

TEST METHOD	TEST DESCRIPTION	TEST RESULT			
		Burn Distance		Time to Flame Out	Critical Radiant Flux
ASTM E648-17a	Critical Radiant Flux	Specimen #1	29.3 cm	10:15 min	0.71 W/cm²
		Specimen #2	21.0 cm	10:05 min	0.85 W/cm²
		Specimen #3	22.3 cm	10:09 min	0.83 W/cm²
		Average	0.80 W/cm²		
	NFPA Classification	Class I			
	STDEV	0.08			
	COF of Variation	9.65%			

Mounting Board: Calcium Silicate Board
Conditioning: 96 hours @ 70°F 50% RH

Adhesive: Shaw 350
Calibration Curve: 361L

Adhesive applied with 3/8" Short Nap Paint Roller
Radiometer #: 5356

Uncertainty:

We undertake all assignments for our clients on a best effort basis. Our findings and judgments are based on the information using the latest test methods available.

TSI can only ensure the test results for the specific items tested.

Unless otherwise noted in the deviations sections of this report, all tests performed are in compliance with stated test method.

Test Report Approval:

Digitally signed by Erle Miles
DN: cn=Erle Miles, o=Testing
Services Inc., ou,
email=erle.miles@tsiinc.com,
c=US
Date: 2018.11.05 13:50:22 -0500

Erle Miles, III, Lab Director Testing Services Inc.

TSI Accreditation:

Our laboratory is accredited by the US Dept. of Commerce, National Institute of Standards and Technology: ISO/IEC 17025:2005.
Our code # is: NVLAP 100108-0.



OUR LETTERS AND REPORTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAR PRODUCTS. THESE LETTERS AND REPORTS ARE FOR THE USE ONLY OF THE CLIENT TO WHOM THEY ARE ADDRESSED AND THEIR COMMUNICATION TO ANY OTHERS OR THE USE OF THE NAME TESTING SERVICES, INC. MUST RECEIVE OUR PRIOR WRITTEN APPROVAL. OUR REPORTS, LETTERS, NAME, SEALS, OR INSIGNIA ARE NOT UNDER ANY CIRCUMSTANCES TO BE USED IN ADVERTISING TO THE GENERAL PUBLIC.

PO Box 2041
Dalton, GA 30722-2041
(706) 226-1400
tsioffice@optilink.us